

Heterogeneous PVC (Dryback)

Format: 1175 (±0.5mm) x 187 (±0.15mm) x 2,5 (±0.1mm) mm
 Carton: 3.955 m²




Usage Classes



Residential - heavy use



Commercial - very heavy use



Industrial - heavy use

Property

Standard

Value

Adhesive Recommendations

	Total Thickness	EN 428 ISO 24346	2,5mm ±0.1mm	 AUS GUTEM GRUND AF 2224 AF 155 AF 180 A2-Zahnleiste
	Wear Layer Thickness	EN 429 ISO 24340	0,70mm ±0.03mm	
	Total Weight	EN 430 ISO 23997	4,3kg/m ²	 Anspruch verbindet D 3307 D 3320 D 3330 D 3125
	Slip Resistance	EN 13893	R10, DS	
	Reaction to Fire	EN 13501-1	Bfl-s1	 ECO PRIM T PRO PLANIPATCH XTRA ULTRAPLAN BASIC XTRA ULTRABOND ECO VS60
	Chair Castor Suitability	EN 425	No damage	
	Furniture Leg Test	EN 424	No damage	 Kiilto Floor Plus Kiilto M1000 ECO
	Impact Sound Reduction	EN 717-2	Δlw = 2db	
	Underfloor Heating	/	Suitable up to 27°C	
	Light Fastness	ISO 105-B02	≤ 6	
	Dimensional Stability	EN 434 ISO 23999	≤ 0,10 %	
	Antistatic Properties	EN 1815	≤ 2 kV when installed on concrete	
	Residual Indentation	EN 433	≤ 0,05 mm	
	Chemical Resistance	EN 423	High resistance	
	Electrical Conductivity	EN 1081	≤ 10Ω	